

GUIBAO 996 NEUTRAL SILICONE SEALANT

General purpose, neutral cure silicone sealant for general sealing, general glazing, waterproofing applications

FEATURES

- One part, neutral cure
- · Easy of application
- Non-corrosive
- Good weatherability and resistance to UV radiation ,heat and humidity, and ozone
- Excellent resistance to temperature extremes, unaffected performance from −50 °C to +150 °C
- Good unprimed adhesion to wide range of substrates
- Good compatibility with other neutral silicone sealants

COLOURS

GUIBAO 996 is available in black, gray, white and other customized colours.

BASIC USES

GUIBAO 996 NEUTRAL SILICONE SEALANT is formulated for weather and waterproofing seal of high-end window & door, and simple curtain wall.

TYPICAL PROPERTIES

These values are not intended for use in preparing specifications.

Test Method	Property	Unit	Standard	Result
GB/T 13477 (ISO 7390)	Slump	mm	€3	0
GB/T 13477 (ISO 8394)	Extrusion rate	ml/min.	≥80	418
GB/T 13477 (ASTM D2377)	Tack free time	h	€3	0.7
GB/T 13477 (ISO 7389)	Extension recovery	%	≥80	90
GB 16776 (ISO 10563)	Weight loss	%	≤10	7
GB/T 13477 (ISO 8339)	Tensile Modulus	MPa	>0.4	0.8
GB/T 13477 (ISO 11600)	Movement capability	%	±25	±25
JC/T 485	Adhesion after UV exposure		No failure	No failure
GB/T 13477 (ISO 8340)	Adhesion at fixed stretch		No failure	No failure
GB/T 13477 (ISO 9047)	Adhesion after heat contract and cold extension		No failure	No failure
GB/T 13477 (ISO 10590)	Adhesion after water immersion		No failure	No failure

*GB: Chinese National Standard

JC/T: Chinese Recommended Standard for Construction Materials

ASTM: American Society for Testing and Materials

ISO: International Standardization Organization

PACKAGING

GUIBAO 996 is available in disposable cartridges (net 300ml), 24 pieces to a carton, and sausages (net 500ml), 20 pieces to a carton.

SPECIFICATIONS

GUIBAO 996 is designed to meet or even exceed the requirement of

Chinese national standard
GB/T 14683-2017-Gn-25HM

STORAGE AND SHELF LIFE

GUIBAO 996 should be stored in original unopened containers. It has a shelf life of 12 months from the date of manufacture.

LIMITATIONS

GUIBAO 996 should not be applied:

- For structural glazing
- To the materials that bleed oils, plasticizers or solvents, such as impregnated wood, oil-based caulks
- In totally confined spaces as sealant requires atmospheric moisture for cure
- To frost laden or damp surfaces
- For continuous water immersion

HOW TO USE

Surface Preparation

Clean all joints removing all foreign matter and contaminants such as oil, grease, dust, water, frost, old sealants, surface dirt, or glazing compounds and protective coatings.

Application Method

Mask areas adjacent to joints to ensure neat sealant lines. Apply GUIBAO 996 in a continuous operation using dispensing guns. Before a skin forms, tool the sealant with light pressure to spread the sealant against the backing materials and joint surfaces. Remove masking tape as soon as the bead is tooled.

TECHNICAL SERVICES

Complete technical information and literature, adhesion testing and compatibility testing are available from Guibao.

SAFETY INFORMATION

- GUIBAO 996 is a chemical product, not edible, no implantation into body and should be kept away from children.
- Cured silicone rubber can be handled without any risk to health.
- Should uncured silicone sealant contact with eyes, rinse thoroughly with water and seek medical treatment if irritation persists.
- Avoid prolonged exposure of skin to uncured silicone sealant.
- Good ventilation is necessary for work and cure places.

DISCLAIMER

The information presented herein is offered in good faith and is believed to be accurate. However, because conditions and methods of using our products are beyond our control, this information should not be used in substitution for customer's tests to ensure that our products are safe, effective, and fully satisfactory for intended specific applications.

Manufacturer

Chengdu Guibao Science and Technology Co., Ltd. No.16, Xinyuan Road, Hi-tech Zone Chengdu, P.R.CHINA

Tel: +86 28 8531 1860 Fax: +86 28 8531 8066

E-mail:guibao@cnguibao.com

www.cnguibao.com